



DESCRIPTION

To see without being seen. The principle of a measured metallization of polyester support forms a reflective screen in the daylight which reflects an image as a mirror, while preserving the transparen...

[read More](#)

Durability: from 12 to 15 years for vertical application in central Europe.

Use: Réfectiv window films are designed for use on any type of clear normal glass

Maintenance after 30 days: with usual cleaning solutions (non-abrasive, without ammonia...). Cleaning products that may scratch the film should be avoided.

Storage: 2 years from delivery. This film should be kept away from excessive humidity and sun rays, at temperatures below 38°C.

Application Method

The glass surface to be glued on has to be free from dust, grease or other contaminants. Some specific materials such as polycarbonate can cause air bubble problems. Therefore, a compatibility test is recommended. For more precision we recommend to [refer back to the application table](#).

Production and standards

In order to constantly improve our production we may change a product colour and manufacturing process without prior notice. Before applying our products we recommend that our users ensure that the film is suitable for the intended use and comply with current standards.

In order to maintain the high level of quality, we do not recommend mixing different film productions when applying films

Material: PET 23 microns

Adhesive: acrylic polymer 13 gr/m²

Liner: siliconized polyester 23 microns

Color:

MIR 501 Gold

MIR 502 Red

MIR 503 Blue

MIR 504 Green

MIR 505 Bronze

Application: internal

UVA Transmission: 5%

Heat Resistance: from -20° to 80°C

Warranty: 2 years

Application Temperature: min. + 5°C

Fire Rating: B-s1,d0

Standards: Euroclasses

Dimensions (of rolls) :

1.52 x 2.5 m

1.52 x 10 m

1.52 x 30 m